



High Tech NxT CARBO Flo 202

High Tech NxT CARBO Flo 202 is a third generation polycarboxylate plasticizer for concrete, developed to obtain ultra-high range water reducing admixture with enhanced workability, durability and impermeability.

It is specially formulated to provide superior performance, increase workability and durability of concrete. High Tech NxT CARBO Flo 202 ensures excellent dispersion, reduced permeability and improved finish. Ideal for all general concrete and reinforced concrete constructions.

ADVANTAGES

- ✓ Reduces water demand to achieve high strength concrete.
- ✓ Higher flowability resulting in excellent workability.
- ✓ Provides high early and long term strengths.
- ✓ Excellent dispersion of steric hindrance of carboxylic ether polymer.
- ✓ Reduces permeability and shrinkage.
- ✓ Improves durability & surface finish.
- ✓ Enhances pumpability of concrete.
- ✓ Reduces the incidence of honeycombing and cold joints during vibration.

TYPICAL PROPERTIES AT 25°C

Appearance	Light brown liquid
Color	Light brown
Specific Gravity	1.20 ± 0.02
Solid Content	20 % ± 2 %
pH Value	5.5 – 7.0
Air Entrainment	0 – 2 %
Dosage Range	0.4 – 2.0 % by wt. of cement
Shelf Life	12 Months

**Typical results under laboratory conditions*



 Susan Road, near P.I.A, Officer Colony 1, office, 38000
 03007888881
 <https://hightechchemicals.com/>



High Tech

NxT CARBO Flo 202



MIXING

Add **High Tech NxT CARBO Flo 202** to the gauging water or to the concrete mixer after the concrete has been batched. Mix for minimum 2 – 3 minutes to achieve uniform dispersion. Do not add more water once the mix starts to set. Mix only that quantity which can be used within 1 – 1.5 hours.

APPLICATION

High Tech NxT CARBO Flo 202 is suitable for all types of concrete where high workability and high early and ultimate strengths are required. It is ideal for ready mix concrete, precast concrete, continuous concreting, slender sections, heavily reinforced concrete and concrete placed in hot weather. Recommended dosage is 0.4 – 2.0 % by weight of cement depending upon the type of cement, mix design and desired workability. Trial mixes are recommended to determine the optimum dosage.

CURING

Proper curing is essential to achieve the desired performance. Cure the concrete by ponding, wet hessian or curing compound immediately after finishing and continue for at least 7 days.

COVERAGE

The dosage range is 0.4 – 2.0 % by weight of cement. Actual dosage depends on mix design, materials and required workability.



Susan Road, near P.I.A, Officer Colony 1, office, 38000



03007888881



<http://hightechchemicals.com/>

SCROLL DOWN FOR PAGE 3 ↓



High Tech NxT CARBO Flo 202

SHELF LIFE

12 months from the date of manufacture when stored in original sealed packaging in a dry and cool place.
Extreme temperature / humidity may reduce shelf life.

PACK SIZE

High Tech NxT CARBO Flo 202 is available in the following pack size.

PACK SIZE	PACKAGING
210 Litre Drum	Bulk
30 KG Drum	Bulk

STORAGE

Store in a cool, dry place away from direct sunlight and frost.
Keep the container tightly closed when not in use.
Do not store in metal containers.

COMPATIBILITY

High Tech NxT CARBO Flo 202 is compatible with all types of Portland cement including OPC, PPC and PSC. It can be used with other High Tech chemical admixtures.

NOTE:

- This product is non-hazardous.
- Avoid contact with eyes and prolonged contact with skin.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice if irritation persists.
- Keep out of reach of children.

